

916**U**L

Product Data Sheet

Clear UL Recognized Polyester Lamination

	United States Units	Metric Units	<u>Test Method</u>
Backing		Polyester (PET)	
Adhesive	Pressure Sensitive Emulsion Acrylic		
Total Thickness	1.6 mil	40 mic	
Film Thickness	1.0 mil	25 mic	
Adhesive Thickness	0.6 mil	15 mic	
Adhesion to Steel	16.3 oz/in	0.43 kg/24mm	ASTM D3330
Tensile Strength	25 lb/in	10.7 kg/24mm	ASTM D3759
Elongation	100%		ASTM D3759
Service Temperature	0°F to 300°F	-18°C to 149°C	
Application Temperature	32°F to 150°F	0°C to 65°C	

Storage Conditions

Store in a clean, dry place at room temperature.

Avoid temperature and humidity extremes.

Complies with FDA regulations 21CFR 175.105 and 21CFR 177.1630

UL Recognized Marking and Labeling System Materials - Component PGGU2.MH47481

Important Notice: All properties are approximate and based on calculations and tests we believe to be reliable. However, the accuracy and completeness are not guaranteed. Before using, user shall determine the suitability of the product for its own use and assumes all risk and liability related to the product. The seller limits its obligations to replacement or at its option, reimbursement of the purchase price of products shown to the seller's satisfaction to have been defective at the time the seller sold it.

www.Qspac.com